



410147 ÎNORADEA, str. Republicii nr. 85/2a

Tel/fax: 0259 ÎN410989

Mobil: 0723 ÎN604799

E-mail: autonom-construct@clicknet.ro

www.autonomconstruct.ro

No.	Denumire produs	Grosime	Tip	Suprafata	Greutate	Flexib.	Stabilit.	Rezistenta la	Alungire la	Ambalaj
		mm	insertie	super/infer	nominala	la rece	termica	tractiune (N)	rupere (%)	mp /
					(kg/m2)	C	C	longit/transv.	longit/transv.	paleta
Membrane bituminoase oxidate										
1	Carton asfaltat A330	0,8	hartie	-/-	0,7	0	60	180/140	2/2	980
2	SINDELIT SR (sub sindrila)	1,5± 0,2	fibra de sticla	nisip/nisip	1,7	0	80	300/200	2/2	450
3	PRIMA V3000	2,5± 0,2	fibra de sticla	nisip/foliePE	2,9	0	80	400/300	2/2	240
4	PRIMA V 3,3 kg	2,7± 5%	fibra de sticla	folie/folie	3,3± 10%	0	80	400/300	2/2	300
5	Prima Oxid V5 Mineral	4± 10%	fibra de sticla	ardezie/foliePE	5± 10%	0	80	400/300	2/2	200
Membrane bituminoase cu bitum modificat (APP)										
6	PRIMAPLAST GV 5 Mineral	4± 5%	fibra de sticla	ardezie/foliePE	5± 10%	-5	140	400/300	2/2	200
7	PRIMAPLAST PV 5 Mineral	4± 5%	poliester	ardezie/foliePE	5± 10%	-5	140	700/550	40/40	200